Hammer Finish 0122 - xxxxx

## **TECHNICAL DATA SHEET**

Name of product:

Type of product:	Hammer finish based on styrene-modified alkyd.	
Application:	Decorative metal coating for interior use, e.g. shop fixtures.	
Properties:	Fast-drying hammer effect enamel. To prevent corrosion, it is absolutely necessary to base coat with primer.	
Solids:	53 weight % 47 vol. %	
Pre-treatment:	Sand blasting in accordance with SA 2½ or chemical pre-treatment in accordance with ISO 8501-1, in addition to, for example, priming with Machine Primer series 0100.	
Application:		
Method:	Recommended viscosity:	Thinner:
Conventional spraying	60 - 65 sec. DIN-cup 4 mm	0700-68063
It is necessary to clean s	pray equipment etc. thoroughly after use to remove re	mnants of silicone.
Drying:		
Dust dry Dry to touch	Drying time Film thickness - dry   30 minutes 20 °C 30 - 50 μm   2 hours 20 °C 30 - 50 μm	
System Specification:		
Primer	1x Esbjerg Machine Primer 0100 - xxxxx 4	0 µm
Top coat	1x Hammer Finish 0122 - xxxxx 4	0 μm
Recommended coating thickness:	Wet film: 85 μm Dry film: 40 μm	
Coverage:	Theoretical: 12 m²/ltr.	
	Store cool and dry	
Storage:	12 Months in an unopened container	
Storage: Shelf-life:	12 Months in an unopened container	
-	12 Months in an unopened container Tools clean with Synthetic Thinner 0700-68063.	
Shelf-life:	-	

This information is based on our present state of knowledge and is intended to provide general notes on our products and their use. It should not, therefore, be construed as guaranteeing specific properties of the product described or its suitability for a particular application. The quality of our products is guaranteed under our General Conditions of Sale.

## Esbjerg Farve- & Lakfabrik A/S Energivej 13 DK- 6700 Esbjerg

Ph. +45 75 12 86 00 FAX +45 75 45 33 68 e-mail: info@esbjergpaints.dk

www.esbjergpaints.dk

Page 1/1 Version no.: 9

en