

## TECHNICAL DATA SHEET

en

Name of product:

### PolyMarine component I 0465 - xxxxx

**Type of product:** 2-pack polyurethane coating. Before use, mix with PolyMarine component II, 0616. PolyMarine component III, 0685 98227 may be added.

**Application:** Solvent-free coating for e.g. ship's ramps.

**Properties:** Weatherproof and hard wearing. Fast curing.

**Solids:** 100 weight %    100 vol. %    Ready to use mixture: Yes

**Pre-treatment:** The base surface should be clean and free of dust.

**Drying:**

	<b>Drying time</b>	<b>Film thickness - dry</b>
Dry to use	24 hours 20 °C	-
Fully cured	3 day(s) 20 °C	-

**Recommended coating thickness:** Wet film: 1.000 µm    Dry film: 1.000 µm

**Coverage:** Theoretical: 1 m<sup>2</sup>/ltr.

**Storage:** Store at minimum. 5°C.

**Shelf-life:** 12 Months in an unopened container

**Note:** Mixing ratio: Please see the can label for information. Potlife 30 minutes @ 20°C.

This information is based on our present state of knowledge and is intended to provide general notes on our products and their use. It should not, therefore, be construed as guaranteeing specific properties of the product described or its suitability for a particular application. The quality of our products is guaranteed under our General Conditions of Sale.

**Esbjerg Farve- & Lakfabrik A/S**

**Energivej 13**

**DK- 6700 Esbjerg**

**Ph. +45 75 12 86 00    FAX +45 75 45 33 68    e-mail: info@esbjergpaints.dk**

**www.esbjergpaints.dk**