

TECHNICAL DATA SHEET**en**

Name of product:

FAXE Floor Laquer / Furniture Laquer 0569**Type of product:** Waterbased self-crosslinking polyurethane / acrylic lacquer.**Application:** For untreated and previously lacquered wooden floors or wooden furnitures, where a very wear resistant and easy-to-maintain surface is desired. It's recommended to apply 3 layers of FAXE Floor Lacquer / Furniture Laquer for optimal wear resistance. Apply a maximum of 2 layers per day.**Properties:** FAXE Floor Lacquer / Furniture Laquer is water based and very durable. The lacquer gives an unmatched wear resistance and makes the finished surface very easy to clean. FAXE Floor Lacquer is used for treating areas with heavy traffic where there are high requirements for the wear resistance. FAXE Floor Lacquer has an outstanding resistance towards spills of common foods and beverages.

Taber Abraser (abrasion resistance):

CS-10: 19 mg

CS-17: 48 mg

Solids: 30 weight % 26 vol. %**Pre-treatment:**

1. Thoroughly cleanse the wood with FAXE Intensive Cleaner and then let the wood dry
2. If the surface has been previously lacquered, the existing layer needs to be sanded down in order to achieve adhesion.
3. In case a white appearance is desired, FAXE Combicolor White can be added (maximum 5 %).
4. To control adhesion and color tone, it's always recommended to test the lacquer on a small area.
5. FAXE Floor Lacquer / Furniture Laquer should be shaken thoroughly before and during use.
6. Apply the lacquer with a brush, roller or spray.
7. The second layer can be applied after approx. 2 hours at 20° C. Remember sanding between layers with 180 grit sandpaper.
8. The lacquer requires a surrounding temp.of at least 15° C. In conditions with high Temperatures above 25° C and low humidity, the drying will be accelerated significantly. In this case, 5 % water can be added to the lacquer to prolong the drying time.

Application:**Method:**

Brush and roller

Spraying

Recommended viscosity:

No thinning required

No thinning required

Thinner:**Drying:**

	Drying time	Film thickness - dry
Dry to use	4-6 hours 20 °C	.
Fully cured	1 weeks 20 °C	.

System Specification:

It's recommended to apply 3 layers of FAXE Floor Lacquer / Furniture Laquer for optimal wear resistance.

Upon wear: Look under pre-treatment, step 2.

Coverage: Theoretical: 10 m²/ltr.**Storage:** Store at temperatures above 10°C.**Shelf-life:** 12 Months in an unopened container

Cleaning:

The tools should be cleaned with water.

CLEANING OF THE FLOOR:

The daily cleaning is only vacuum cleaning. When the wood is dirty, it could be cleaned with FAXE GOlak Care.

CLEANING OF THE FURNITURE:

The daily cleaning is just a wet cloth.

This information is based on our present state of knowledge and is intended to provide general notes on our products and their use. It should not, therefore, be construed as guaranteeing specific properties of the product described or its suitability for a particular application. The quality of our products is guaranteed under our General Conditions of Sale.

EFApaint A/S, Energivej 13, DK-6700 Esbjerg

TLF. +45 75 12 86 00

e-mail: info@efapaint.dk

www.efapaint.dk